needlona®	**PPS/PPS 504 glaze**	
TAN:	7880	
Composition		
web:	Polyphenylene Sulphide	
scrim:	Polyphenylene Sulphide	
Area Weight [g/m²]: BWF Envirotec standard 04	500	
Thickness [mm]: BWF Envirotec standard 01	1.5	
Density [g/cm³]: BWF Envirotec standard 01	0.33	
Air Permeability ISO 9237:1995		
[mm/s @ 200 Pa]:	250	resp. 150 l/(dm² min) @ 200 Pa
Tensile Strength ISO 9073-3:1989		Sample size 200 mm/50 mm,
length [N]:	1,100	Sampling parallel to the scrim threads,
cross [N]:	1,300	Deformation rate 200 mm/min
Temperature Resistance		
cont. [°C]:	≤ 190	Chemical gas stream conditions may require
peak [°C]:	≤ 200	a lower continuous operating temperature to be maintained
Properties:	» heat set » glazed face side	

The technical data refer to new goods, are determined based on relevant standards and/or BWF Envirotec standards and apply within the context of our tolerances which can be consulted at www.bwf-envirotec.com/tolerances. No claims whatsoever are justified by this datasheet. Any recourse to courts of law is excluded. Any persons using this datasheet consent to this agreement.

At our German site, we are certified under the ISO 9001 quality management system, the ISO 14001 environmental management system and the BS OHSAS 18001 occupational health and safety management system. At our Chinese site, we are certified under the ISO 9001 quality management system.